

Supra IXPE 1mm 405 kPa

Underlay for vinyl and SPC floors 3in1


3in1 underlay with integrated adhesive tape and vapor barrier



5,83 m²




1,1x5,3 m




1,0 mm



IS < 19 dB



CS < 405 kPa



R < 0,065 m²K/W

	Test Method	Unit	Value	General Result
Weight	ISO 23997:2012	Kg/m ²	±0.2	0.2
Thickness	EN 823:2013	mm	±0.1	1.0
Length	EN 823:2013	mm	-1%, +5%	5300
Width	EN 823:2013	mm	-1%, +2.5%	1100
Tensile Strength (TD)	ISO 1798:2008	MPa	≥1.6	2.0
Elongation (TD)	ISO 1798:2008	%	≥230	300
Tensile Strength (MD)	ISO 1798:2008	MPa	≥1.8	2.4
Elongation (MD)	ISO 1798:2008	%	≥250	320
Compressive Strength, Compression	EN 16354:2013	kPa	≥220	405
Tear Strength (TD)	ISO 34-1:2014	N/mm	≥3.5	9.5
Tear Strength (MD)	ISO 34-1:2014	N/mm	≥2.5	7.5
Thermal Resistance	EN 12667:2001	(W/m*K)	±0.005	0.065
Impact Sound Improvement	ISO 10140-2:2007	dB	±2	17



8 594187 733407